

## Erratum

**Unravelling the Iron Age glass trade in southern Italy: the first trace-element analyses.** by SONIA CONTE, ROSSELLA ARLETTI, FRANCESCA MERMATI and BERNARD GRATUZE (2016, vol. 28, p. 409–433, DOI: 10.1127/ejm/2016/0028-2516)

\* Corresponding author, e-mail: [sonia.conte@unimore.it](mailto:sonia.conte@unimore.it)

The published Table 3 was erroneously typeset. The correct version of Table 3 is given in the following pages, with apologies of the journal for any inconvenience.

Table 3. Trace elements composition obtained by LA-ICPMS on the analysed samples (in ppm). \* = analysed in Orléans at the IRAMAT center. n.a. = not analysed.

Sample	Chemical Type	B*	Ti	V	Cr	Co	Ni	Cu	Zn	Ga	Rb	Sr	Y	Zr	Nb	Sn	Sb	Ba
SN18r	High-Al	4447	3246	51.3	44.6	27.8	20.9	24.5	44.6	10.8	59.3	185	24.2	230	10.7	2.4	1.1	930
SN18bl		4202	3376	53.7	45.2	25.0	20.5	26.3	45.6	11.0	57.6	173	21.8	185	10.5	2.3	2.0	743
SN22bl		4327	4338	68.6	52.7	9.6	25.6	59.8	78.4	15.5	60.2	286	26.0	207	12.7	3.1	1.7	458
SN19bl	High-Fe-Pb	48.2	1132	158	86.3	4.6	50.3	259	8547	10.5	14.1	173	12.2	59.5	3.4	174	882	172
SN5inc	Plant Ash	114	198	5.7	6.1	1.1	7.4	20.6	29.5	0.6	4.9	343	1.2	8.9	0.5	0.7	1846	39
SN12inc		112	505	11.9	18.0	2.4	9.7	16.7	24.4	1.3	10.5	374	2.4	16.3	1.4	1.2	2989	42.4
SN13inc		117	450	10.8	15.5	2.3	9.1	7.9	21.9	1.2	13.6	395	2.4	16.5	1.3	1.1	14.8	30.3
SN14g		133	490	12.8	14.7	2.6	10.6	11.5	29.9	1.3	7.3	318	2.3	16.1	1.3	0.9	100	32.9
SN15inc		131	485	12.1	14.8	2.5	10.6	12.9	27.3	1.3	7	313	2.3	15.8	1.3	0.9	1482	32
SN36g		115	584	16.0	16.5	2.9	11.2	24.5	35.1	1.4	9.1	446	3.2	20.7	1.5	0.8	1010	77.2
SN28inc		127	192	5.2	7.8	1.0	7.6	11.2	34.5	0.6	5.1	323	1.4	8.3	0.6	0.9	2827	37.5
SN16inc		120	502	11.9	17.3	2.4	10.5	14.5	27.3	1.3	9.9	356	2.2	14.7	1.3	1.1	3016	41.3
SN17inc		116	442	9.5	10.1	2.5	9.4	19.1	30.1	1.3	8.7	329	3.1	14.2	1.3	1	2154	48.4
SN29inc		111	241	8.7	8.3	1.5	8.3	13.7	28.6	0.9	5.8	264	1.8	12.8	0.8	1	2293	56.5
SN27t		122	338	9.4	17.3	2.1	10.4	12.1	30	1.2	6.0	446	2.6	15.1	1.0	1.3	1.1	76.5
SN11b		123	347	9.5	12.6	86.8	66	4763	80.2	1.0	5.9	341	2.9	18.4	1.0	14.1	1731	84.9
CA9inc*		140	297	8.6	n.a.	2.6	14.6	16.7	28.4	1.6	4.8	385	2.4	15.5	0.9	6.2	3126	68.1
CA10inc*		191	213	7.5	n.a.	1.4	7.1	19.6	19	1.8	5.7	206	1.6	11.2	0.6	2.8	3991	36.2
CA12inc*		150	431	11.4	n.a.	2.6	11.8	20.7	29.6	1.6	5.8	198	2	14.9	1.3	4.6	1216	53.9
CA14inc*		86.3	139	3.2	n.a.	0.5	2.6	18.4	9.9	0.5	3	258	0.9	8.7	0.3	2.4	7	41.5
CA15I*		134	360	14.4	n.a.	2.8	14.7	5386	31.8	1.9	4.8	234	1.6	12.1	1.1	70.3	52.4	47.1
CA17b*	80.7	263	7.5	n.a.	2.9	11.8	6734	106	0.9	12.2	322	1.2	6.0	0.6	93.9	35.2	43.1	
SN37t	Natron	123	376	9.5	9.8	2.9	6.6	65.29	9.1	0.7	2.3	295	4.4	87.6	1.0	1	1.1	58.2
SN25b		102	175	11.6	3.9	3.8	21.8	9255	40.6	0.6	4.1	159	2	19.0	0.5	105	11	58.1
SN34b		132	817	7.9	16.7	696	383	10459	112	1.9	9.9	276	4.5	253	2.1	14.3	6.2	40.4
SN35t		95	352	3.6	7.6	192	53.5	7350	54.8	2.0	3.9	191	4.3	75.6	0.9	34.3	4.8	27.8
SN38t		176	1762	21.4	42.4	3.7	8.9	111	10.6	0.8	1.7	181	5.5	837	4.4	2.2	2.7	81.5
SN32g*		78.5	317	3.8	10.1	1.1	6.7	2.9	4.3	0.6	0.6	235	3.9	82.1	0.9	6.2	<0.1	21.7
SN4t		123	450	9.6	8.8	2.8	5.5	58.1	9.0	0.6	1.6	275	4	104	1.1	1.1	1.8	48.7
SN7t		195	620	14.9	11.7	3.5	10	10005	15.4	0.8	14.1	265	4.1	122	1.5	22.4	36.2	69.9
SN9g		<0.1	430	6.7	9.7	1.4	3.1	33.8	8.1	0.6	0.9	205	3.9	75.7	1.0	0.6	2	54.8
SN3inc		159	1727	19.1	39.6	3.2	7.8	106	7.8	0.8	1.8	179	5.4	783	4.1	2.3	2.7	77.6

(continued)

Table 3. (Continued).

Sample	Chemical Type	B*	Ti	V	Cr	Co	Ni	Cu	Zn	Ga	Rb	Sr	Y	Zr	Nb	Sn	Sb	Ba	
SN33a	Natron	163	504	9.7	12.5	1.3	3.8	9.2	13.3	1.0	1.7	344	4.5	87.5	1.3	2.5	1.4	48	
SN52g*		115	533	12.9	13.9	4.3	11.5	5644	7.0	1.2	1.0	118	3.5	125	1.5	66.8	44.4	56.5	
CA13inc*		106	279	4.8	n.a.	1.1	3.6	21.0	9.7	0.7	2.4	171	1.6	35.4	0.8	2.5	22.2	29.7	
SN21bl	Black	102	564	17.1	35	2.0	12.3	36.3	198	1.6	4.6	97.3	6.7	37.4	1.5	3.9	152	57.2	
SN31bl		1090	983	56.3	13.6	1.6	12.9	62.3	748	2.6	14.1	72.0	7.7	44.3	3.0	0.9	62.2	49.9	
SN30bl		<0.1	997	27.4	15.4	3.4	12.4	168	265	2.65	1.7	8.8	57.8	3.6	45.7	2.9	0.9	1211	25.7
SN39bl*		975	900	62.1	64.4	4.6	74.1	138	138	98.5	2.3	12.4	154	6	44.4	3.1	8.0	788	53.5
SN41bl*		1017	1385	32.5	<0.1	9.9	126	215	215	110	3.2	11	41.4	6.7	67.6	3.5	6.9	53.1	18.1
SN10bl		78.3	1587	48.2	79.6	6.4	36.4	145	145	73.5	4.4	17.7	204	8.1	71.1	4.1	2.5	40.1	158
CM2bl*		747	1030	28.2	n.a.	1.0	7.9	647	242	2.6	2.6	9.6	27.6	4	31.7	3.1	6.2	10.9	8.3
CM3bl*		1285	1034	125	n.a.	19.3	194	60.2	19.9	3.4	14.6	73.1	4.9	4.9	25.9	2.5	6.7	n.d	19.5
CM6bl*		1121	964	25.6	n.a.	1.7	9.7	33.6	369	3.1	12.7	36.8	7.9	7.9	49.9	3.6	9.1	2.7	36.7
CM9bl*		908	829	23.4	n.a.	9.4	11.1	429	1061	2.4	9.1	20.8	7.2	7.2	62.6	2.5	11.2	19.8	58.4
CM10bl*		828	835	24.4	n.a.	9.5	10	563	709	2.5	10.1	26.3	8.4	8.4	69.1	2.6	13.1	8.3	42
CM11bl*		1004	1088	22.2	n.a.	1.5	13.1	41.8	845	2.5	11.5	14.3	5.6	5.6	55.6	3.6	2.8	557	10.3
CM15bl*		1619	1479	35.9	n.a.	7.3	138	39.1	11.1	3.4	14.2	55.9	5.9	5.9	53.5	4.1	8.8	n.d	4.9
CM16bl*		1553	1555	46.6	n.a.	6.8	105	82.3	24.8	3.7	15.7	62.2	7	7	58.7	4.7	4.4	n.d	42.9
CM19bl*		1073	1157	34.5	n.a.	8.4	169	102	40.7	3.3	12.5	28.7	5.3	5.3	29.3	3.1	16.8	1.5	n.d
SN2b		Al-Co-blue	201	263	6.8	6.9	836	599	21	824	1.1	3.9	44.6	13.2	10.6	0.7	1	4.2	42.1
SN23b			216	514	7.0	7.4	346	425	222	389	0.9	4.8	126	21.6	44.6	1.4	1	7.5	31.3
SN1b	139		209	5.5	5.8	1568	1174	190	1965	0.8	2.9	57	9.3	8.7	0.6	1.9	1.4	32.6	
SN40b*	219		173	6.8	3.6	1766	781	201	1053	1.1	3.7	35.8	8	6.1	0.5	4.6	1	28.4	
SN42b*	232		308	6.9	5.8	1280	775	207	887	3.3	3.7	50.7	11.8	11.6	0.9	3.8	332	33.7	
SN47b*	103		235	6.9	5.5	478	369	133	371	1.2	2.7	132	4.2	12.8	0.7	2.9	5.4	31.3	
SN49b*	221		360	8.0	7.5	596	467	247	642	1.7	13.1	121	8.1	10.1	1.0	10.1	862	35.4	
SN50b*	255		269	6.1	4.8	1238	770	16.3	875	2.2	1.9	40.3	12.8	14.1	0.8	5.2	1.7	30.1	
CA5b*	111		239	6.2	n.a.	415	376	35.4	333	1.5	1.8	138	7	12.8	0.7	5.3	4.9	30.1	
CA7b*	141		165	4.8	n.a.	364	416	5.2	321	1.4	0.6	129	8.5	10.3	0.4	5.9	20.3	24.9	
CA8b*	293		407	8.9	n.a.	383	324	1525	408	2.5	4.1	112	12.1	24.2	1.2	10.7	146	42.2	
CA18b*	214		513	7.9	n.a.	367	447	76.8	292	2.2	2.1	95.4	13.8	35.4	1.4	2.7	8.1	22.1	

(continued)

Table 3. (Continued).

Sample	Chemical Type	La	Ce	Pr	Nd	Sm	Tb	Dy	Ho	Er	Tm	Yb	Lu	Hf	Ta	Pb	Th	U	
SN18r	High-Al	23.7	46.6	5.2	22.1	4.6	0.7	4.4	0.9	2.7	0.4	2.9	0.4	5.8	0.8	14.1	6.8	5.1	
SN18bl		22.2	44.7	5.0	21.1	4.4	0.6	4.1	0.9	2.4	0.4	2.7	0.4	5.1	0.7	13.5	6.7	5.2	
SN22bl		30.5	53.1	6.5	26.6	5.5	0.7	4.5	0.9	2.5	0.4	2.7	0.4	4.9	0.8	23.8	8.3	4.3	
SN19bl	High-Fe-Pb	38.5	16.7	6.9	24.9	4.2	0.4	2.4	0.5	1.2	0.2	1.2	0.2	1.6	0.2	163500	3.5	17.6	
SN5inc	Plant Ash	1.3	2.6	0.3	1.3	0.3	<0.1	0.2	<0.1	0.1	<0.1	0.1	<0.1	0.2	<0.1	11.7	0.3	0.3	
SN12inc		3.8	19.3	1.0	4.1	0.8	0.1	0.5	0.1	0.3	<0.1	0.3	<0.1	0.4	0.1	5.5	0.6	0.6	
SN13inc		3.4	21.1	0.9	3.6	0.7	0.1	0.5	0.1	0.2	<0.1	0.2	<0.1	0.4	0.1	2.5	0.5	0.3	
SN14g		3.2	16.4	0.7	2.9	0.6	0.1	0.4	0.1	0.2	<0.1	0.2	<0.1	0.4	0.1	2.2	0.5	0.3	
SN15inc		3.1	16.8	0.7	3.0	0.6	0.1	0.5	0.1	0.2	<0.1	0.2	<0.1	0.4	0.1	2.7	0.5	0.3	
SN36g		5.1	15.2	1.2	5.0	0.9	0.1	0.6	0.1	0.3	<0.1	0.3	<0.1	0.5	0.1	6.4	0.6	0.3	
SN28inc		1.7	6.1	0.4	1.7	0.3	<0.1	0.3	0.1	0.1	<0.1	0.1	0.1	<0.1	0.2	<0.1	2.3	0.3	0.9
SN16inc		3.6	18.7	1.0	4.0	0.7	0.1	0.5	0.1	0.2	<0.1	0.3	<0.1	0.4	0.1	4.4	0.5	0.6	
SN17inc		3.5	6.4	0.8	3.6	0.7	0.1	0.6	0.1	0.3	<0.1	0.3	<0.1	0.4	0.1	5.3	0.5	0.9	
SN29inc		2.0	5.3	0.4	1.9	0.4	0.1	0.3	0.1	0.2	<0.1	0.2	<0.1	0.3	0.1	2.7	0.4	0.6	
SN27t		3.9	25.4	1.0	4.0	0.7	0.1	0.5	0.1	0.2	<0.1	0.2	<0.1	0.4	0.1	16	0.5	0.6	
SN11b		3.3	13.7	0.8	3.6	0.8	0.1	0.6	0.1	0.3	<0.1	0.3	<0.1	0.5	0.1	165	0.6	0.7	
CA9inc*		3.5	18.0	0.8	3.4	0.6	0.1	0.4	0.1	0.3	<0.1	0.2	<0.1	0.3	0.1	n.a.	0.4	0.4	
CA10inc*		2.4	14.7	0.6	2.2	0.4	<0.1	0.3	0.1	0.2	<0.1	0.2	<0.1	<0.1	<0.1	n.a.	0.2	0.9	
CA12inc*		3.1	12.8	0.7	3	0.7	0.1	0.4	0.1	0.2	<0.1	0.2	<0.1	<0.1	0.4	0.1	n.a.	0.4	0.6
CA14inc*		0.8	1.9	0.2	0.8	0.2	<0.1	0.1	<0.1	<0.1	0.1	<0.1	0.1	<0.1	0.2	<0.1	n.a.	0.2	0.2
CA15I*		2.3	12	0.6	2.4	0.4	0.1	0.3	0.1	0.2	<0.1	<0.1	0.2	<0.1	0.3	0.1	n.a.	0.4	0.8
CA17b*	1.4	2.9	0.3	1.3	0.2	<0.1	<0.1	0.2	<0.1	0.1	<0.1	0.1	<0.1	0.1	<0.1	n.a.	0.2	0.1	
SN37t	Natron	4.4	5.4	0.9	4	0.8	0.1	0.7	0.2	0.4	0.1	0.4	0.1	2.1	0.1	8.8	0.5	0.9	
SN25b		2.2	3.2	0.5	2	0.4	0.1	0.3	0.1	0.2	<0.1	<0.1	<0.1	0.5	<0.1	1.3	0.3	0.4	
SN34b		5	6	1	4.4	0.8	0.1	0.7	0.2	0.4	0.1	0.5	0.1	5.7	0.2	64.8	0.8	2.2	
SN35t		5.7	4.7	1.1	4.5	0.9	0.1	0.6	0.1	0.3	0.1	0.3	0.1	1.7	0.1	33.5	0.5	0.9	
SN38t		4	5.1	0.8	3.6	0.7	0.1	0.8	0.2	0.6	0.1	0.8	0.2	17.4	0.3	22	1	1	
SN32g*		4.2	5.4	0.8	3.7	0.6	0.1	0.6	0.1	0.4	<0.1	<0.1	0.3	<0.1	1.8	0.1	<0.1	0.5	1.7
SN4t		3.9	4.8	0.8	3.5	0.7	0.1	0.6	0.1	0.4	0.1	0.4	0.1	2.4	0.1	11.5	0.5	1	
SN7t		3.9	5.4	0.8	3.5	0.7	0.1	0.6	0.1	0.4	0.1	0.4	0.1	2.9	0.1	41.7	0.7	2.1	
SN9g		4.3	4.6	0.8	3.6	0.7	0.1	0.6	0.1	0.4	0.1	0.4	0.1	1.8	0.1	12.2	0.5	2.6	
SN3inc		4.1	5.4	0.9	3.5	0.7	0.1	0.8	0.2	0.6	0.1	0.8	0.1	17	0.3	22.8	1	1.1	

(continued)

Table 3. (Continued).

Sample	Chemical Type	La	Ce	Pr	Nd	Sm	Tb	Dy	Ho	Er	Tm	Yb	Lu	Hf	Ta	Pb	Th	U	
SN33a	Natron	4.7	6.7	1	4.2	0.8	0.1	0.7	0.1	0.4	0.1	0.4	0.1	2	0.1	1.8	0.6	2.1	
SN52g*		3.5	5.1	0.7	3.1	0.6	0.1	0.5	0.1	0.3	<0.1	0.4	0.1	2.6	0.1	218	0.6	1.8	
CA13inc*		1.7	4.1	0.4	1.5	0.3	<0.1	0.2	0.1	0.1	0.1	<0.1	0.2	<0.1	0.7	n.a.	0.3	0.5	
SN21bl	Black	7.4	11.6	1.5	5.9	1.1	0.2	1	0.2	0.6	0.1	0.6	0.1	1	0.1	4544	1.5	2.7	
SN31bl		12.6	24.2	2.8	12	2.2	0.3	1.5	0.3	0.8	0.1	0.7	0.1	1.2	0.2	4.3	5.0	2.2	
SN30bl		7.3	13.6	1.5	6.2	1.1	0.1	0.7	0.2	0.4	0.1	0.5	0.1	1.3	0.2	25.3	2.9	1.5	
SN39bl*		8.6	15.2	1.8	7.5	1.6	0.3	1.1	0.2	0.7	0.1	0.7	0.1	1	0.2	51.8	2.8	1.1	
SN41bl*		7.4	11.7	1.5	7	1.3	0.3	1.3	0.2	0.8	0.1	0.7	0.1	1.7	0.2	<0.1	2.3	0.5	
SN10bl		11.6	19.5	2.4	9.5	1.8	0.2	1.6	0.3	0.9	0.1	1	1	0.1	1.8	0.2	9143	3.6	4.7
CM2bl*		7.3	12.4	1.3	5.7	1.1	0.1	0.7	0.1	0.3	<0.1	0.4	0.4	<0.1	0.8	0.2	n.a.	2.6	1.8
CM3bl*		6.6	12.7	1.4	6.1	1.1	0.2	0.8	0.2	0.4	0.1	0.3	0.3	0.1	0.6	0.1	n.a.	1.5	1
CM6bl*		9.6	18	2.1	9.9	2	0.4	1.6	0.3	1	0.1	0.7	0.1	1.2	0.2	n.a.	3.2	1.6	
CM9bl*		9.6	18	2.2	10.2	2.0	0.4	1.4	0.3	0.9	0.1	0.7	0.1	1.5	0.2	n.a.	3.4	1.1	
CM10bl*		11.2	18.1	2.4	11.3	2.4	0.5	1.6	0.3	1.1	0.1	0.9	0.1	1.7	0.2	n.a.	3.6	1.1	
CM11bl*		8.2	15.7	1.6	6.8	1	0.2	0.9	0.2	0.6	0.1	0.7	0.1	1.3	0.2	n.a.	2.6	1.5	
CM15bl*		7.4	14.4	1.5	6.4	1.4	0.2	1	0.2	0.6	0.1	0.7	0.1	1	0.2	n.a.	2.8	1.4	
CM16bl*		12.2	25.1	2.7	11.8	2.1	0.2	1.4	0.3	0.7	0.1	0.7	0.1	1.5	0.3	n.a.	5	1.2	
CM19bl*		8.4	15.4	1.7	7.5	1.4	0.1	1.1	0.2	0.4	0.1	0.6	0.1	0.5	0.1	n.a.	2.3	0.7	
SN2b		Al-Co-blue	2.7	8.3	1.6	9.5	2.8	0.5	2.5	0.5	1.2	0.2	1.1	0.2	0.3	0.1	2.6	0.9	0.6
SN23b	5.8		14.2	2.6	15.7	4.7	0.8	4.4	0.8	2.1	0.3	1.7	0.3	1.1	0.1	6.9	1.6	1.7	
SN1b	2.2		7.9	1.5	7.7	2	0.3	1.7	0.3	0.9	0.1	0.8	0.1	0.2	<0.1	19.7	1.0	3.8	
SN40b*	1.1		7	1.1	7.1	2.3	0.4	1.6	0.3	0.9	0.1	0.5	0.1	0.1	<0.1	<0.1	0.4	2	
SN42b*	2.8		10.7	1.8	9.8	2.8	0.4	2.1	0.4	1.1	0.1	1	0.1	0.1	0.3	6.8	1	0.6	
SN47b*	1.6		5.7	0.7	3.3	0.8	0.1	0.7	0.1	0.4	0.1	0.3	<0.1	<0.1	0.3	0.3	0.5	0.5	
SN49b*	2.2		9.4	1.2	5.9	1.7	0.3	1.5	0.3	0.7	0.1	0.7	0.1	0.2	<0.1	13.1	0.6	1	
SN50b*	2.6		9.8	1.7	9.7	2.8	0.4	2.3	0.4	1.1	0.1	1	0.1	0.3	<0.1	0.7	1	0.6	
CA5b*	1.7		6.5	1	5	1.5	0.2	1.3	0.2	0.8	0.1	0.7	0.1	0.2	<0.1	n.a.	0.4	0.4	
CA7b*	1.6		6.1	1	6.4	2	0.3	1.7	0.3	0.8	0.1	0.7	0.1	0.2	<0.1	n.a.	0.9	0.8	
CA8b*	3.7		11.9	1.9	11.2	3.2	0.5	2.6	0.4	1.1	0.1	0.8	0.1	0.6	0.1	n.a.	1.1	0.7	
CA18b*	4.2		14.5	2.1	11.1	3.2	0.5	2.9	0.5	1.4	0.2	1.2	0.2	0.8	0.1	n.a.	1.1	2.1	